



EURASIA PETROL
Trading of Petroleum Products

PRODUCT DATA SHEET

Product Category	Product Name	Grade
Polymers	PVC	65

	PVC RESIN		
TYPE	S-65	S-67	S-70
Appearance	W.P	W.P	W.P
Inherent Viscosity	0.85-0.91	0.91-0.95	0.98-1.02
K-Value	64-66	66-68	69-71
Particle Size % Retained on 40 Mesh % Retained on 200 Mesh	Nil =>85	Nil =>85	Nil =>85
Porosity (ML/GR)	0.1-0.26	0.12-0.28	0.2-0.32
Volatile Matter (Heat Loss) % Max	0.7	0.7	0.7
Bulk Density (GR/CC) (Apparent)	0.46-0.60	0.45-0.57	0.44-0.5
Dark Resin (Per10 SQ.IN.)	0-10		0-10

Application	The rigid form of PVC is used in construction for pipe and in profile applications such as doors and windows. It is also used for bottles, other non-food packaging, and electric cables.
Packaging	25 Kg plastic bag.



+90 24 22 44 55 85



www.Eurasiapetrol.com
Info@Eurasiapetrol.com



Adnan menderes blv, Tahıl pazarı neighborhood,
Emka building, no:22, Muratpaşa, Antalya, Turkey.